
वस्त्रादि — वायु आकाशीय प्रयोजनों के लिए
नॉइलान टेप — विशिष्टि
(दूसरा पनरीक्षण)

**Textiles — Nylon Tapes for
Aerospace Purposes — Specification**
(Second Revision)

ICS 49.025.60

© BIS 2023



भारतीय मानक ब्यूरो
BUREAU OF INDIAN STANDARDS
मानक भवन, 9 बहादुर शाह ज़फर मार्ग, नई दिल्ली - 110002
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI - 110002
www.bis.gov.in www.standardsbis.in

FOREWORD

This Indian Standard (Second Revision) was adopted by the Bureau of Indian Standards, after the draft finalized by the Textiles Materials for Aeronautical and Related Products Sectional Committee had been approved by the Textiles Division Council.

Nylon has special properties like low density and high strength, so it is mostly used textile fibre in aerospace applications. Nylon tapes woven on either shuttle loom or needle loom is used in reinforcement/fabrication of parachutes and other aerial delivery equipment. Needle looms are capable of inserting the double number of wefts compared with the shuttle looms, hence the tapes woven on needle loom has higher cover factor.

This standard was first published in 1967 and subsequently revised in 1979. This revision has been made in the light of experience gained since its last revision and to incorporate the following major changes:

- a) The requirements for nylon tapes woven on needle loom has been incorporated;
- b) Packing and sampling clauses have been modified; and
- c) The references to Indian Standards have been updated.

The composition of the committee responsible for the formulation of this standard is listed in Annex B.

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS 2 : 2022 'Rules for rounding off numerical values (*second revision*).’ The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

*Indian Standard***TEXTILES — NYLON TAPES FOR AEROSPACE PURPOSES —
SPECIFICATION***(Second Revision)***1 SCOPE**

1.1 This standard covers nylon tapes of 14 mm, 19 mm, 25 mm, 25.4 mm, 32 mm, 38 mm, and 44 mm widths, generally used in the fabrication of parachutes and other aerial delivery equipment.

1.2 This standard specifies the requirements for nylon tapes woven on shuttle loom and needle loom.

2 REFERENCES

The standards listed in Annex A contain provisions which through reference in this text, constitute provisions of this standard. At the time of publication, the editions, indicated were valid. All standards are subject to revision and parties to agreements based on this standard are encouraged to investigate the possibility of applying the most recent editions of the standards listed in Annex A.

3 MATERIAL

3.1 The material of the yarn, that is Nylon 6/ Nylon 6 6, shall be identified by microscopic and dissolution test as given IS 667.

3.2 Multifilament, bright and high tenacity nylon yarn as specified in Table 1 and Table 2 shall be used in manufacture of nylon tapes. The twist in the resultant yarn shall not be less than 100 per metre both for warp and weft.

4 TYPES

4.1 Based on the type of loom, on which the nylon tapes are woven shall be classified as under:

- a) *Type I* — Nylon tapes woven on shuttle

loom; and

- b) *Type II* — Nylon tapes woven on needle loom.

5 REQUIREMENTS

5.1 The nylon tapes woven on shuttle loom shall meet the physical requirements as given in Table 1 and the nylon tapes woven on needle loom shall meet the physical requirements as given in Table 2.

5.1.1 In case of needle loom (*Type II*), the selvage shall be made firm with interlocking thread.

5.1.2 The tapes shall be uniformly woven with firm and regular selvages in 2/2 herring bone twill weave with one reversal. The nylon tapes shall be free from weaving defects and stains.

5.1.3 In order to illustrate or specify the indeterminable characteristics, such as general appearance, lustre, feel and shade, a sample has been agreed upon and sealed, the supply shall be in conformity with the sample in such respects.

5.2 The tapes shall further meet the chemical requirements as specified in Table 3.

5.2.1 The tapes shall be free from tendering substances.

5.2.2 Dyed Tapes

Acid/disperse dyes may be used; however, metallized/chrome dyes shall not be used [*see IS 4472 (Part 3)*].

Table 1 Physical Requirements of Nylon Tapes Woven on Shuttle Loom (Type I)
(Clauses 3.2 and 5.1)

Sl No.	Width, mm	Length /Roll	Warp, Tex	Weft, Tex	Thickness, mm, <i>Max</i>	Ends in Full Width, <i>Min</i>	Picks/ dm, <i>Min</i>	No. of Plies (see Note 3)		Mass, <i>Max</i> g/m	Breaking Load on Full Width × 20 cm, kgf, <i>Min</i>	Elongation at Break, Percent, <i>Min</i>
								Warp	Weft			
(1)	(2)	(3)	(see Note 3) (4)	(see Note 3) (5)	(6)	(see Note 3) (7)	(see Note 3) (8)	(9)	(10)	(11)	(see Note 2) (12)	(see Note 2) (13)
i)	14 ± 1	66 m, unless otherwise specified in contract or order.	23	23	1.0	87	127	2	4	8.7	230	18
ii)	19 ± 1		23	23	0.8	142	141	1	2	6.2	193	18
iii)	25 ± 1		23	23	0.8	71	127	4	2	11.2	400	18
iv)	25.4 ± 1.6 (see Note 1)		23	23	0.76	120	180	1	2	6.0	137	14
v)	32 ± 1		23	23	0.8	89	127	4	2	14.2	506	18
vi)	38.0 ± 1.5		23	23	0.8	106	127	4	2	16.8	605	18
vii)	44.0 ± 1.5		23	23	0.8	125	127	4	2	19.6	705	18
Tolerance	—	—	+10 percent –5 percent	+10 percent –5 percent	—	—	—	—	—	—	—	—
Method of Test, Ref to	IS 1954	—	IS 7703 (Part 1)		IS 7702 under a pressure of 200 gf/cm ²	IS 1963		—		IS 1964	IS 1969 (Part 1)	

Table 2 Physical Requirements of Nylon Tapes Woven on Needle Loom (Type II)

(Clause 3.2 and 5.1)

Sl No.	Width, mm	Length /Roll	Warp, Tex,	Weft, Tex	Thickness, mm	Ends in Full Width, Min	Picks/ Dm, Min	No. of Plies (see Note 3)		Mass, Max, g/m	Breaking Load on Full Width × 20 cm, kgf, Min (see Note 2)	Elongation at Break, Percent, Min (see Note 2)
			(see Note 3)	(see Note 3)	Max	(see Note 3)	(see Note 3)	Warp	Weft			
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)	(12)	(13)
i)	14 ± 1	66 m, unless otherwise specified in contract or order.	23	23	1.0	87	254	2	2	8.7	230	18
ii)	19 ± 1		23	23	0.8	142	282	1	1	6.2	193	18
iii)	25 ± 1		23	23	0.8	71	254	4	1	11.2	400	18
iv)	25.4 ± 1.6 (see Note 1)		23	23	0.76	120	360	1	1	6.0	137	14
v)	32 ± 1		23	23	0.8	89	254	4	1	14.2	506	18
vi)	38.0 ± 1.5		23	23	0.8	106	254	4	1	16.8	605	18
vii)	44.0 ± 1.5		23	23	0.8	125	254	4	1	19.6	705	18
Tolerance	—	—	+10 percent –5 percent	+10 percent –5 percent	—	—	—	—	—	—	—	—
Method of Test, Ref to	IS 1954	—	IS 7703 (Part 1)		IS 7702 under a pressure of 200 gf/cm ²	IS 1963		—		IS 1954	IS 1969 (Part 1)	

NOTES

1 This is special light variety for high cover factor.**2** In case of dyed tapes 5 percent relaxation shall be allowed to the values given in mass per unit length and extension at break.**3** If yarn of 46 or 93 tex is used, number of plies of warp and weft shall be suitably modified.

Table 3 Chemical Requirements of Nylon Tapes
(Clause 5.2)

Sl No.	Characteristics	Requirements	Methods of Test, Ref to
(1)	(2)	(3)	(4)
i)	pH value of aqueous extract	6.0 to 8.5	IS 1390
ii)	Colour fastness to (in case of coloured cords):		
	a) Light	5 or better	IS/ISO 105-B02
	b) Washing, Test C (3)	4 or better	IS/ISO 105-C10

6 MARKING

6.1 Each roll shall bear a securely attached label with the following information:

- Name of the material and its net mass (g);
- Length (m), Width (mm), Thickness (mm);
- Type; and
- Name/trade-mark of the manufacturer and the year of manufacture.

6.2 BIS Certification Marking

The nylon tape rolls conforming to the requirements of this standard may be certified as per the conformity assessment schemes under the provisions of the *Bureau of Indian Standards Act, 2016* and the Rules and Regulations framed thereunder, and the nylon tape rolls may be marked with the Standard Mark.

7 PACKING

7.1 Unless otherwise agreed to between the buyer and the seller, the nylon tapes shall be packed as given in **7.2**.

7.2 An appropriate number of rolls shall be arranged in a cylindrical bundle and secured by jute twine to form a pack. A suitable number of such packs shall be arranged and wrapped with polyethylene film of at least 100 microns thickness (*see* IS 2508) and placed in a wooden packing case of adequate strength, previously lined with one layer of waterproof packing paper conforming to Type 2 of IS 1398. The empty spaces, if any, in the packing case shall be stuffed with cushioning materials to

avoid damage in transit. The case shall be bound by iron hoops or wires. The gross mass of the case shall not exceed 40 kg.

7.3 Each case shall be marked with the consignment details as provided in the contract or order in addition to the markings given in **6.1**.

8 SAMPLING

8.1 Lot

The quantity of nylon tape of the same type and width in a consignment shall constitute a lot.

8.2 Unless otherwise specified in the contract or order, the sampling plan given in Table 4 shall be followed.

8.2.1 Rolls shall be selected at random (*see* IS 4905).

8.2.2 Sub-sample rolls specified in col (5) of Table 4 shall be drawn from the sample rolls selected according to col (3) of the Table 4.

9 NUMBER OF TEST SPECIMENS AND CRITERIA FOR CONFORMITY

9.1 Number of test specimens and criteria for conformity shall be as given in Table 5.

9.2 For breaking load and elongation test, an additional 2 m test sample from each of the sample rolls remaining after drawing the subsample (*see* **8.2.2**) shall be taken if so, specified in the contract.

Table 4 Scale of Sampling
(Clause 8.2)

SI No.	No. of Rolls in the Lot	Sample Size	Permissible No. of Defective Rolls in Respect of Tests on Sample Rolls	Sub-Sample Size	Permissible No. of Defective Rolls in Respect of Tests on Sub-sample Rolls
(1)	(2)	(3)	(4)	(5)	(6)
i)	Up to 25	3	0	3	None
ii)	26 - 100	5	0	4	
iii)	101 - 150	8	0	5	
iv)	151 - 300	13	0	7	
v)	301 - 500	20	1	8	
vi)	501 - 1 000	50	1	9	
vii)	Above 1 000	80	2	10	

Table 5 Number of Test Specimens and Criteria for Conformity
(Clause 9.1)

SI No.	Characteristics	Number of Samples	Criteria for Conformity
(1)	(2)	(3)	(4)
i)	Length, linear density width, mass, thickness, ends, picks and plies	According to col (3) of Table 4.	Non-conforming rolls not to exceed corresponding number given in col (4) of Table 4.
ii)	Breaking load, elongation, pH value, colour fastness	According to col (5) of Table 4.	All the rolls to satisfy the relevant requirements.

ANNEX A

(Clause 2)

LIST OF REFERRED STANDARDS

<i>IS No.</i>	<i>Title</i>	<i>IS No.</i>	<i>Title</i>
IS 667 : 1981	Methods for identification of textile fibres (<i>first revision</i>)	IS 2508 : 2016	Polyethylene films and sheets — Specification (<i>third revision</i>)
IS 1390 : 2022	Textiles — Determination of pH of aqueous extract (<i>third revision</i>)	IS 4472 (Part 3) : 2021	Textile dyestuffs — Identification of the application classes of dyes on textile materials (<i>first revision</i>)
IS 1398 : 1982	Specification for packing paper water proof, Bitumen-laminated (<i>second revision</i>)	IS 7702 : 2012	Textiles — determination of thickness of textiles and textile products (<i>first revision</i>)
IS 1954 : 1990	Determination of length and width of woven fabrics — Methods (<i>second revision</i>)	IS 7703 (Part 1) : 1990	Methods of test for man-made fibres continuous filament flat yarn: Part 1 Linear density (<i>first revision</i>)
IS 1963 : 1981	Method for determination of threads per unit length in woven fabrics (<i>second revision</i>)	IS/ISO 105-B02 : 2014	Textiles — Tests for colour fastness Part B04 Colour fastness to artificial weathering: Xenon arc fading lamp test
IS 1964 : 2001	Textiles — Methods for determination of mass per unit length and mass per unit area of fabrics (<i>second revision</i>)	IS/ISO 105-C10 : 2006	Textiles — Tests for colour fastness: Part C10 Colour fastness to washing with soap or soap and soda
IS 1969 (Part 1) : 2018	Textiles — Tensile properties of fabrics: Part 1 Determination of maximum force and elongation at maximum force using the strip method (<i>fourth revision</i>)		

ANNEX B
(Foreword)

COMMITTEE COMPOSITION

Textile Materials for Aeronautical and Related Products Sectional Committee, TXD 13

<i>Organization</i>	<i>Representative(s)</i>
Aerial Delivery Research and Development Establishment, Agra	DR MANOJ KUMAR (Chairperson)
Aerial Delivery Research and Development Establishment, Agra	SHRI GAURAV SINGH SHRI PRASANTA KUMAR MALLIK (<i>Alternate</i>)
Atul Aakash Merchants Pvt Ltd, Mumbai	SHRI K. C. J. MODY SHRI ATUL K. MODY (<i>Alternate</i>)
Defence Materials and Stores Research and Development Establishment, Kanpur	SHRI BISWA RANJAN
Directorate General of Civil Aviation, New Delhi	SHRI LALIT GUPTA SHRI HILLOL BISWAS (<i>Alternate</i>)
Garware Technical Fibres Ltd, Pune	SHRI KISHOR J. DARDA SHRI S. J. CHITNIS (<i>Alternate</i>)
Indian Rayon and Industries Limited, Rishra	SHRI A. N. CHOUDHARY SHRI ABHEY NAIR (<i>Alternate</i>)
Kusumgar Corporates, Mumbai	SHRI SIDDARTHA Y. KUSUMGAR DR M. L. TALUKDAR (<i>Alternate</i>)
Madura Coats Limited, Mumbai	SHRI S. K. RAJA SHRI VIVEK RAJ (<i>Alternate</i>)
Ministry of Defence (DGQA), New Delhi	SHRI R. K. S. DECCA JAG SHRI S. S. KASHYAP (<i>Alternate</i>)
Ministry of Defence (DGAQA), New Delhi	SHRI DALJEET SINGH DR SUBHASH (<i>Alternate</i>)
Motilal Dulichand Pvt Ltd, Kanpur	SHRI SUNIL PRAHLADKA SHRI SHAILENDRA NATH MISRA (<i>Alternate</i>)
Office of the Textile Commissioner, Mumbai	SHRI AJAY PIANDIT SHRI JAMIL AHMAD (<i>Alternate</i>)
Ordnance Parachute Factory, Kanpur	SHRI K. K. TOPPO SHRI SACHIN KHORIA (<i>Alternate</i>)
Oriental Synthetic and Rayon Mills Pvt Ltd, Navi Mumbai	SHRI SMITI YEOLE
RCMA, Kanpur	SHRI P. K. SHUKLA SHRI ALOK KUMAR (<i>Alternate</i>)
S R F Limited, Chennai	SHRIMATI ANGELINA DIVYA SHRI ANKUR SHARMA (<i>Alternate</i>)
Spica Elastic Limited, Pune	SHRI MANISH R. JAITHA SHRI SOHRAB BHARUCHA (<i>Alternate</i>)

Thanawala & Co, Mumbai	SHRI HEMAL M. THANAWALA SHRI VIVAAN THANAWALA (<i>Alternate</i>)
The Synthetic and Art Silk Mills Research Association, Mumbai	DR MANISHA MATHUR SHRI ASHWINI SUDAM
Todi & Company Ltd, Mumbai	SHRI S. P. TODI SHRI ADARSH TODI (<i>Alternate</i>)
UP Textile Technology Institute, Kanpur	DR MUKESH KUMAR SINGH PROF PRASHANT (<i>Alternate</i>)
Urja Products Limited, Ahmedabad	SHRI ANSHUL J. NANAVATY SHRI JANAK G. NANAVATY (<i>Alternate</i>)
Vardhman Yarn and Threads Ltd, Gurugram	SHRI ANU HANDA
Vikram Sarabhai Space Centre, Thiruvananthapuram	DR SANTHOSH B. SHRI ANIL PENULY (<i>Alternate</i>)
Viraj Syntex Pvt Limited, Kanpur	SHRI AMIT SINGH
BIS Directorate General	SHRI J. K. GUPTA SCIENTIST 'E'/DIRECTOR AND HEAD (TEXTILES) [REPRESENTING DIRECTOR GENERAL (<i>Ex-officio</i>)]

Member Secretary
SHRI BANOTHU RANGA
SCIENTIST 'B'/ASSISTANT DIRECTOR
(TEXTILES), BIS

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 2016* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Head (Publication & Sales), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the website- www.bis.gov.in or www.standardsbis.in.

This Indian Standard has been developed from Doc No.: TXD 13 (19707).

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002

Telephones: 2323 0131, 2323 3375, 2323 9402

Website: www.bis.gov.in

Regional Offices:

	Telephones
Central : 601/A, Konnectus Tower -1, 6 th Floor, DMRC Building, Bhavbhuti Marg, New Delhi 110002	{ 2323 7617
Eastern : 8 th Floor, Plot No 7/7 & 7/8, CP Block, Sector V, Salt Lake, Kolkata, West Bengal 700091	{ 2367 0012 2320 9474
Northern : Plot No. 4-A, Sector 27-B, Madhya Marg, Chandigarh 160019	{ 265 9930
Southern : C.I.T. Campus, IV Cross Road, Taramani, Chennai 600113	{ 2254 1442 2254 1216
Western : Plot No. E-9, Road No.-8, MIDC, Andheri (East), Mumbai 400093	{ 2821 8093

Branches : AHMEDABAD. BENGALURU. BHOPAL. BHUBANESHWAR. CHANDIGARH. CHENNAI. COIMBATORE. DEHRADUN. DELHI. FARIDABAD. GHAZIABAD. GUWAHATI. HIMACHAL PRADESH. HUBLI. HYDERABAD. JAIPUR. JAMMU & KASHMIR. JAMSHEDPUR. KOCHI. KOLKATA. LUCKNOW. MADURAI. MUMBAI. NAGPUR. NOIDA. PANIPAT. PATNA. PUNE. RAIPUR. RAJKOT. SURAT. VISAKHAPATNAM.